

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Fyber Flooring
Suite 302,
35 Buckingham Street
Surry hills NSW 2010

Test Number : 22-004692
Issue Date : 13/12/2022
Print Date : 16/12/2022
Order Number : Chevron

Sample Description Clients Ref : "Chevron"
Wilton Loop pile carpet tested on Dunlop Springtred Ultimate Underlay
Colour : Grey/Cream
End Use : Residential and Commercial Use
Nominal Composition : 100% Pure New Wool
Nominal Mass per Unit Area/Density : 2730g/m2
Nominal Thickness : 7.0mm



285755

61720

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved




Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.




Chris Campbell

APPROVED SIGNATORY


MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Fyber Flooring
Suite 302,
35 Buckingham Street
Surry hills NSW 2010

Test Number : 22-004692
Issue Date : 13/12/2022
Print Date : 16/12/2022
Order Number : Chevron

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 23-11-2022

Date Tested 12-12-2022

CHF Value	1	2	3	Mean
Length	10.2	-	-	- kW/m ²
Width	5.6	6.7	6.3	6.2 kW/m ²

Smoke Value	1	2	3	Mean
Length	35	-	-	- % .min
Width	31	34	37	34 % .min

Each specimen was loose laid over Dunlop - Springtred Ultimate (Gold) underlay and 6mm thick fibre reinforced cement board and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

285755

61720

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR